



Technical

Specifications

PALE OIL 100

PARAMETERS	TEST METHOD	UNITS	GUARANTEED	TYPICAL
Color ASTM	ASTM D 6045	-	1.0	L1.0
Kinematic viscosity at 40 °C	ASTM D 445	mm ² /s	20-24	22.8
Kinematic viscosity at 100 °C	ASTM D 445	mm ² /s	Report	3.7
Pour point	ASTM D7346	°C	Max -35	
Flash point (COC)	ASTM D 93	°C	Min 166	173
Density at 15 °C	ASTM D 4052	kg/m ³	Report	0,92
Sulfur	ASTM D 2622	wt%	Max 100	
API Gravity, 60F	ASTM D 4052	F		22.5
Specific Gravity	ASTM D 4052	F	0.907-0.923	0.919
Aniline Point	ASTM D 611	°C	68-74	71
Refractive Index	ASTM D 1747			1.4949

Handling Health & Safety :

Lubricants consisting of highly refined mineral oils with specification additives. In normal conditions of use, this lubricant presents no particular toxic hazard. All lubricants, of any kind should be handled with great care, particularly avoiding can contact with the skin.

Prevent any splashing, and keep away from combustible materials. Store under cover and away from any risk of pollution. Dispose off the used oil correctly; don't pour down drains, into watercourses or the soil.

İNOVATİF MAKİNA PETROL LOJİSTİK İTHALAT
İHRACAT SANAYİ VE TİCARET LİMİTED ŞİRKETİ
KÜME EVLERİ TRAK DEPOLARI NO : 444 İÇ KAP / NO 6 MERKEZ / EDİRNE
V.D. : KIRKPINAR VKN : 663 094 0035



ASTM INTERNATIONAL